

Dissolving Softwood Pulp

PERFORMANCE 95-630 C



Salzachtalstraße 88, 5400 Hallein – Austria
 Phone: +43(0)6245 890 – 340
 Email: sales@austrocel.com
 www.austrocel.com

PARAMETER	UNIT	SPEC	TYPICAL	TEST METHOD
Viscosity	ml/g	600-660	632	SCAN-C15:99
R18	%	≥ 95.0	95.2	DIN 54355
Alpha	%	≥ 93.0	93.3	Calculation
Brightness	% ISO	≥ 92.0	93.1	ISO 3688/2470
Ash (-Na)	%	≤ 0.10	0.07	ISO 2144
Fe	ppm	≤ 2	0.7	ICP-OES
Mn	ppm	≤ 0.20	0.05	ICP-OES
Na	ppm	-	385	ICP-OES
CaO	ppm	≤ 80	22	ICP-OES
Cu	ppm	≤ 0.20	0.05	ICP-OES
Mg	ppm	≤ 100	55	ICP-OES
SiO ₂	ppm	≤ 60	25	ICP-OES
Acetone-Extractive	%	≤ 0.10	0.08	EN ISO 14453
Dirt	#/m ²	≤ 15	6	Internal
Moisture	%	8.5	8.6	EN ISO 638
Basis Weight	g/m ²	650	651	ISO 536
Sheet Density	g/cm ³	0.65	0.66	ISO 534

PERFORMANCE 95-630 C

- High quality dissolving pulp made by environmentally friendly techniques and totally chlorine free (TCF) bleaching
- Tailor made product for **Specialty** application like **CMC, Ether, Nitro**, etc.
- The basic raw material is spruce wood (softwood) from sustainably managed forests (PEFC) in the European Union
- A highly skilled work force controls process stability as well as quality consistency
- Bale Dimension: 730 x 645 x 500 mm, 200 kg
 Reel Dimension: Diameter max. 1.200 mm, Width max. 900 mm, Weight max. 650 kg

Status: 11/2016

We add value to wood.

